

PC2P **PC2 (Melamine) - PRIMER** **Page 1 of 1**

- FEATURES**
- Based on a durable 1k melamine resin system
 - Fast drying for speedy production schedules
 - Excellent opacity & sanding. Easily re-coatable
 - PC2 (Melamine) Primer may be used under our PC, AC & PU Systems

USES Interior joinery & furniture.

TOPCOAT	PC1-6-AA000-005	PC1 Promatch
	PC2-6-AA000-005	PC2 (Melamine) Promatch
	CA2-6-AA000-005	AC2-Lo (low odour) Promatch
	RP1-6-AA000-005	RP1 (Fast Dry PU) Promatch
	SPU-6-AA000-005	SIRCA (530 Type PU) Promatch

BASECOAT	PC2-7-10320-005	PC2 MDF Primer (Melamine) WHITE
	PC2-7-BL010-005	PC2 MDF Primer (Melamine) BLACK
	PC2-7-CH010-005	PC2 MDF Primer (Melamine) CHARCOAL
	PC2-7-GR010-005	PC2 MDF Primer (Melamine) GREY

THINNER FOR SYSTEM	CL2-9-TH031-005	No 31 Anti Bloom Retarding Thinners
	PCT-9-TH000-005	PCT Pre-Catalysed Thinners

CLEANER FOR EQUIPMENT	CL2-9-TH020-005	ISF Spray Gun & Brush Cleaner
------------------------------	-----------------	-------------------------------

APPLICATION EQUIPMENT Conventional airless / airmix or HVLP spray equipment.

APPLICATION Thin with PCT Thinners as required up to a maximum of 10% by volume. Apply a light coat of PC2 Primer, allow to dry, de-nib. Apply another coat of PC2 Primer as necessary. Then, after a further de-nib, apply a full even coat of PC, AC or PU Top Coats (Please refer to Top Coat Technical Data for further application information)

FURTHER INFORMATION Please note the use of any Third party Top Coat systems will require testing and should not be assumed that they are compatible. ISF recommended Top Coats have been tested for FIRA 6250 General & Severe Use where applicable.

Please note: This product can also be supplied in 400 ml Aerosols with professional adjustable fan nozzels.



Coverage	Touch Dry	Recoat Time	Max Resistance	Pot Life	Mix Ratio	Shelf Life	Pack Size
10-12 Sq.m/lt	20-30 mins	60 mins	Overnight	N/A	N/A	12 months	5 & 25lt

